



Primer PU60 and Thinner PU

– Polyurethane moisture curing solvent resin for consolidating and waterproofing cementitious screeds

– Thinner for Primer PU60

WHERE TO USE

Primer PU60:

Waterproofing of absorbent cementitious screeds where the residual moisture is above the recommended level for laying wooden flooring.

Thinner PU:

A special blend of solvents for diluting **Primer PU60**.

Some application examples

- Consolidation of screeds that are mechanically weak due to defects, moisture or lack of binder.
- Insulation primer for substrates in anhydrite or gypsum.
- Anti-dust consolidating impregnator for industrial concrete floors or for surfaces where raised floors are to be laid.
- Waterproofing treatment before the laying of wooden flooring to block the rise of excessive residual damp in the screeds.
- Anti-dust treatment for both cementitious and anhydrite screeds with irregular surfaces.
- Preparation of synthetic mortars.

TECHNICAL CHARACTERISTICS

Primer PU60 is a one-component polyurethane solvent resin which sets due to the moisture which is present in the surrounding air and in the screeds, and which has the property of penetrating well into the support. After evaporation of the solvent and the product is set, the

surface layer of the substrate becomes more solid, harder and abrasion resistant. The efficiency of the primer increases more as the amount of penetration increases. Therefore, it is advisable to dilute the first coat with **Thinner PU** from 25% to 100% according to the absorbency of the screed.

RECOMMENDATIONS

- **Primer PU60** must only be diluted with **Thinner PU**.
- Do not use on wet surfaces and where the rise of water due to capillary action is present.
- Do not apply smoothing compounds or adhesives if the surface of **Primer PU60** is shiny (spread dry sand on the primer while it is still damp). If **Primer PU60** has already set, it must be briskly sanded down.
- **Primer PU60** is inflammable. All precautions must be taken to avoid the risk of fire. Use the product in areas where there is good ventilation to avoid the formation of pockets of fumes given off by the solvent and do not use naked flames, avoid sparks and do not smoke.
- If successive treatments with synthetic resin-based products are to be carried out, wait until the solvent has completely evaporated off. Any solvent which has not evaporated off and is held in the substrate, could damage the characteristics of the successive treatment.
- Heated anhydrite screeds and substrates must not be waterproofed. Therefore, do not use **Primer PU60** if the residual moisture is above the recommended level.

Primer PU60 and Thinner PU

PRIMER PU60 - TECHNICAL DATA (typical values)	
PRODUCT IDENTIFICATION	
Consistency:	liquid
Colour:	brown
Density (kg/l):	1.025
Max. allowed humidity for waterproofing:	5% measured with a carbide hygrometer
Mixing ratio:	none. Damp-setting mono-component
Dilution:	from 25% to 100% with Thinner PU
Yield:	400-1200 g/cm ² according to the absorbency of the support material and the number of coats applied
Set to light foot traffic at +23°C and 50% R.H.:	according to yield and dilution, 3-8 hours
Setting time at +23°C and 50% R.H.:	24 hours
Waiting time before bonding:	when there is no odour of solvent, usually after 2-7 days with reactive adhesives such as Lignobond , Ultrabond P902 2K and Ultrabond P990 1K
Application temperature range:	from +5°C to +35°C
Packaging:	10 kg drums
Application:	with a roller, brush or watering can
Storage:	in its sealed, original packaging in a temperature range between +5°C and +25°C, the product is stable for 12 months
Cleaning:	with Thinner PU while the product is still fresh
Hazard classification according to Directive 99/45/CE:	flammable, hazardous. Before using, carefully read the information contained in the safety data sheet
THINNER PU - TECHNICAL DATA (typical values)	
PRODUCT IDENTIFICATION	
Consistency:	liquid
Colour:	clear
Density (kg/l):	0.871
Viscosity FC4":	12"
Storage:	12 months
Hazard classification according to Directive 99/45/CE:	highly flammable, hazardous. Before using, carefully read the information contained in the safety data sheet
Customs class:	3814 00 10

APPLICATION PROCEDURE

1 - Waterproofing and consolidation

The screed must be free of oil, wax and dirt in general and must be cured for at least 7 to 10 days for every cm of thickness in the case of traditional screeds. Where quick-hydration screeds are used, the curing time must be according to that recommended for the product.

Cracks and crazing must be opened and repaired with **Eporip** or **Eporip Turbo**.

At least two coats of **Primer PU60** must be applied by using a roller or a brush. In order to promote good penetration of the first coat, dilute the product with **Thinner PU** at a ratio of 1:1 to 1:4 according to the absorbency of the support material. After four hours, apply the second coat with the same dilution ratio. If the treatment is not uniform, another coat of neat product may be applied as soon as the previous coat may be stepped on (and after no more than 18 hours). Before passing on to the successive phase, wait until the solvent has completely evaporated off, which usually takes 2 to 7 days. In order to promote good bonding of the adhesive or smoothing compound, it is advisable to sprinkle clean, dry sand on the final coat while it is still fresh.

2 - Anti-dust treatment

Dilute **Primer PU60** with **Thinner PU** at a ratio of 2:1 in weight and apply it with a roller or a brush in a single coat. Wait until it dries (approximately 24 hours) before carrying out the successive phase.

3 - Repair operations

For small smoothing-off and crack-repair operations, a mix of **Primer PU60** blended with **Mapequarz** may be used. The mix ratio is 7-8 kg of **Mapequarz** for every kg of **Primer PU60**. The mortar obtained is easy to apply, and once it sets it gives a very sound surface to which any kind of parquet may be applied. The **Primer PU60** and **Mapequarz** mix must be applied on surfaces which have been treated beforehand with diluted **Primer PU60** no more than 18 hours before. For successive bonding, only reactive adhesives such as **Lignobond**, **Ultrabond P902 2K** and **Ultrabond P990 1K** must be used.

Cleaning

Primer PU60 may be removed while it is still fresh with **Thinner PU**. Once it has set, it is difficult to remove, but sometimes good results may be obtained with **Pulicol**.

CONSUMPTION

Primer PU60

400-1200 g/m².

Thinner PU:

0.25-1 kg per kg of **Primer PU60**.

PACKAGING

Primer PU60:

Available in 10 kg metal drums.

Thinner PU:

Available in 9 kg metal drums.

STORAGE

Primer PU60 and Thinner PU:

12 months if stored in their original, tightly-sealed containers and kept under normal conditions.

SAFETY INSTRUCTIONS FOR APPLICATION OF THE PRODUCT

Primer PU60:

The product is inflammable. If it is inhaled or comes into contact with the skin, there may be an allergic reaction.

Do not apply the product in the presence of naked flames, lit cigarettes or sparks. Avoid inhaling the fumes and avoid the product coming into contact with the eyes and skin. Only use the product in well-ventilated areas. For further information, please consult the safety data sheet.

PRODUCT FOR PROFESSIONAL USE.

Thinner PU:

The product contains highly inflammable, hazardous solvents. Do not use in the vicinity of naked flames, lit cigarettes or electrical appliances which may give off sparks. Do not inhale the fumes and use only in well-ventilated areas.

Wear protective gloves. For further information, please consult the safety data sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

While the indications and guidelines contained in this data sheet correspond to the company's knowledge and wide experience, they must be considered, under all circumstances, merely as an indication and subject to confirmation only after long-term, practical applications. Therefore, anybody who undertakes to use these products, must ensure beforehand that they are suitable for their intended application and, in all cases, the user is to be held responsible for any consequences deriving from their use.

**All relevant references
of the product are available
upon request**

**Primer PU60
and Thinner PU**



BUILDING THE FUTURE

**MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS
(Quality, Environment and Safety)**

MAPEI S.p.A. - ITALY				MAPEI FAR EAST Pte Ltd MAPEI MALAYSIA SDN BHD		MAPEI s.r.o. - CZECH REP	
MAPEI FRANCE	MAPEI INC - CANADA	RESCON MAPEI AS - NORWAY		MAPEI Kft. - HUNGARY	MAPEI ARGENTINA S.A.	MAPEI SUISSE SA	

www.mapei.com

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

549-1-2004

(GB) A.G. BETA